

PROHLÁŠENÍ O VLASTNOSTECH



DoP: 0118

pro fischer Power-Fast II vruty (Vrtuy pro dřevěné konstrukce) - CS

1. Jedinečný identifikační kód typu výrobku: DoP: 0118

2. Zamýšlené/zamýšlená použití: Pro spojování v nosných dřevěných konstrukcích nebo pro upevnění nadkrokevní tepelné izolace

- 3. Výrobce: fischerwerke GmbH & Co. KG, Klaus-Fischer-Straße 1, 72178 Waldachtal, Německo
- 4. Zplnomocněný zástupce: --
- 5. Systém/systémy POSV: 3
- 6. Evropský dokument pro posuzování: EAD 130118-01-0603

Evropské technické posouzení: ETA-19/0175; 2020-01-07

Subjekt pro technické posuzování: ETA-Danmark A/S

7. Deklarovaná vlastnost/Deklarované vlastnosti:

Mechanická odolnost a stabilita (BWR 1), Charakteristická pevnost na mezi kluzu (BWR 4)

- Rozměry: Viz. dodatek, zejména Přílohy 12, 13, 14
- Charakteristický plastický moment : Viz. dodatek, zejména Příloha 5
- Ohybový úhel: Viz. dodatek, zejména Příloha 1
- Charakteristická pevnost na vytažení: Viz. dodatek, zejména Přílohy 5, 6, 7
- Charakterická odolnost proti protažení hlavy vrutu: Viz. dodatek, zejména Příloha 7
- Charakteristická pevnost v tahu: Viz. dodatek, zejména Příloha 3
- Charakteristická pevnost na mezi kluzu: Viz. dodatek, zejména Příloha 5
- Charakteristická pevnost v krutu: Viz. dodatek, zejména Příloha 3
- Moment vložení: Viz. dodatek, zejména Příloha 3
- Rozteče vrutů či závitových tyčí a jejich vzdálenosti k okraji a ke konci a minimální tloušťka tesařského prvku:
 Viz. dodatek, zejména Přílohy 8, 9, 22
- Modul prokluzu vrutů a závitových tyčí zatížených převážně osovým zatížením: Viz. dodatek, zejména Příloha 8
- Odolnost proti korozi: Viz. dodatek, zejména Přílohy 1, 10, 12, 13, 14

Bezpečnost v případě požáru (BWR 2)

Odolnost proti ohni: Vrty splňují požadavky třídy A1

8. Příslušná technická dokumentace a/nebo specifická technická dokumentace: ---

Vlastnosti výše uvedeného výrobku jsou ve shodě se souborem deklarovaných vlastností. Toto prohlášení o vlastnostech se v souladu s nařízením (EU) č. 305/2011 vydává na výhradní odpovědnost výrobce uvedeného výše.

Podepsáno za výrobce a jeho jménem:

Thilo Pregartner, Dr.-Ing.

Wolfgang Hengesbach, Dipl.-Ing., Dipl.-Wirtsch.-Ing.

ppa. The Mx

i.V. W. Kglal

Tumlingen, 2020-02-17

- Toto PoV bylo připraveno v různých jazykových mutacích.. V případě rozporu vždy rozhoduje interpretace verze v anglickém jazyce.
- Příloha obsahuje nepovinné a doplňkové informace v anglickém jazyce na rámec zákonných požadavků.

II SPECIFIC PART OF THE EUROPEAN TECHNICAL ASSESSMENT

1 Technical description of product and intended use

Technical description of the product

"fischer Power-Fast II" screws are self-tapping screws to be used in timber structures. They shall be threaded over a part of the length or over the whole length. The screws shall be produced from carbon steel wire for nominal diameters between 3,0 mm and 6,0 mm. Where corrosion protection is required, the material or coating shall be declared in accordance with the relevant specification given in Annex A of EN 14592.

Geometry and Material

The nominal diameter d (outer thread diameter) of the screws shall not be less than 3,0 mm and shall not be greater than 6,0 mm.

The overall length l_s of the screws, shall not be less than 20 mm and shall not be greater than 300 mm. Dimensions see Annex A.

The ratio of inner thread diameter to outer thread diameter d_1/d ranges from 0,50 to 0,80.

The screws are threaded over a minimum length l_g of 4,0 \cdot d (i.e. $l_g \ge 4,0 \cdot$ d).

The thread pitch p (distance between two adjacent thread flanks) ranges from 0,50 ·d to 0,85 ·d.

No breaking shall be observed at a bend angle of $\alpha \le (45/d^{0.7} + 20)^\circ$.

2 Specification of the intended use in accordance with the applicable EAD

The screws are used for connections in load bearing timber structures between members, softwood and hardwood of: Solid timber, glued laminated timber, cross-laminated timber (CLT) and laminated veneer lumber, similar glued members, wood-based panels or steel. "fischer Power-Fast II" screws with a thread over the full length can also be used as tensile or compressive reinforcement perpendicular to the grain or as shear reinforcement. Furthermore "fischer Power-Fast II" screws with diameter of 6 mm may also be used for fixing of thermal insulation on rafters and on vertical facades. Steel plates and wood-based panels except solid wood panels and EGGER Eurostrand OSB 4 TOP, laminated veneer lumber and CLT, shall only be fixed on the side of the screw head.

The following wood-based panels may be used:

- Plywood according to EN 636 or European Technical Assessment or national provisions that apply at the installation site
- Particleboard according to EN 312 or European Technical Assessment or national provisions that apply at the installation site
- Oriented Strand Board according to EN 300 or European Technical Assessment or national provisions that apply at the installation site
- Fibreboard according to EN 622-2 and 622-3 or European Technical Assessment (minimum density 650 kg/m³) or national provisions that apply at the installation site
- Cement bonded particleboard according to EN 634 or European Technical Assessment or national provisions that apply at the installation site
- Solid wood panels according to EN 13353 or European Technical Assessment or national provisions that apply at the installation site
- Wood-based panels for use in constructions according to EN 13986
- Cross laminated timber according to European Technical Assessment
- Laminated Veneer Lumber according to EN 14374 or European Technical Assessment
- Engineered wood products according to European Technical Assessment, provided that the ETA for the product provides provisions for the use of selftapping screws and these provisions are applied

The screws shall be driven into softwood and hardwood with a maximum characteristic density of 730 kg/m³ without pre-drilling or after pre-drilling (see Table 1 and Table 2) with a diameter not larger than the inner thread diameter for the length of the threaded part and with a maximum of the smooth shank diameter for the length of the smooth shank.

Tuble 1. Recommen	иси ргс-игши	ig ulumeters				
Nominal diameter	Bore-hole diameter [mm]					
d [mm]	Softwood Hardwood					
3,0	2,0	2,5				
3,5	2,0	2,5				
4,0	2,5	3,0				
4,5	2,5	3,0				
5,0	3,0	3,0				
6,0	4,0	4,0				

Table 1: Recommended pre-drilling diameters

Recommended values without pre-drilling for the maximum penetration length of the threaded part of "fischer Power-Fast II" made of carbon steel in wood based members like ash, beech and oak or LVL

according to ETA-14/0354 (e.g. Baubuche) are shown in Table 2.

 Table 2: Recommended penetration length without predrilling in hardwood

<i>ci</i> , <i>i</i> , <i></i>	is in nai anooa
Nominal diameter	Maximum penetration
d [mm]	length [mm]
3,0	40
3,5	45
4,0	50
4,5	60
5,0	70
6,0	70

The hole diameter in steel members must be pre-drilled with a suitable diameter.

In connections with screws with countersunk head according to Annex A the head must be flush with the surface of the connected structural member. A deeper countersunk is not allowed.

Pan head screws according to Annex A may be used together with washers according to EN ISO 7094.

The intended use of the screws is in timber connections for which all requirements of mechanical resistance, stability and safety in use in the sense of the Basic Works Requirements 1 and 4 of Regulation 305/2011 (EU) shall be fulfilled.

"fischer Power-Fast II" screws with $d \ge 4,5 \text{ mm}$ can be driven in with standard screw driver and with impact screw drivers too (e.g. fischer FSS 18V 400 BL or fischer FSS 18V 600). It is also recommended to use, especially in combination with steel plates, torque controlled tools e.g. torque wrenches.

The design of the connections shall be based on the characteristic load-carrying capacities of the screws.

The design capacities shall be derived from the characteristic capacities in accordance with Eurocode 5 or an appropriate national code. The screws are intended for use for connections subject to static or quasi-static loading.

The zinc-coated screws are for use in timber structures subject to the moisture content of internal conditions defined by the service classes 1 and 2 regarding to EN 1995-1-1:2014.

The provisions made in this European Technical Assessment are based on an assumed intended working life of the screws of 50 years.

The indications given on the working life cannot be interpreted as a guarantee given by the producer or Assessment Body, but are to be regarded only as a means for choosing the right products in relation to the expected economically reasonable working life of the works.

Char	acteristic	Assessment of characteristic					
3.1	Mechanical resistance and stability*) (BWR1)					
Tensi	le strength		Characteristic value <i>f</i> _{tens,k} :				
1 01101		Power-Fast II	d=3,0 mm	3,2 kN			
			d = 3,5 mm	4,1 kN			
			d = 4,0 mm	5,2 kN			
			d = 4,5 mm	6,3 kN			
			d = 4,5 mm d = 5,0 mm				
				8,9 kN			
			d= 6,0 mm	13,1 kN			
Torsi	onal strength		Ratio of the charact	eristic torsional strengt			
	C		to the mean insertio				
			$f_{tor,k} / R_{tor,mean} \ge 1,5$				
			Characteristic value	from h			
		Power-Fast II	d=3,0 mm	1,5 Nm			
		1 Owel-1 ast II	d=3,5 mm	2,0 Nm			
			d = 4,0 mm	3,0 Nm			
			· ·	· · · · · · · · · · · · · · · · · · ·			
			d = 4,5 mm	4,2 Nm			
			d= 5,0 mm	6,0 Nm			
			d= 6,0 mm	10,0 Nm			
3.2	Safety in case of fire (BWR2)						
React	ion to fire		performance class	603/EC, amended b			
3.3	Safety in use (BWR4)		See aspects covered	l by BWR1			
3.4	General aspects related to the perfor product ^{*)}	rmance of the	satisfactory durabi when used in time timber species des	een assessed as having ility and serviceabilit per structures using th cribed in EN 1995-1- conditions defined b d 2.			
Identification		See Annex A					
	al and special application area		See Annex B				
*) 800	additional information in section 3.5 to 3	37					

3 Performance of the product and references to the methods used for its assessment

3.5 Mechanical resistance and stability

The load-carrying capacities for the "fischer Power-Fast II" screws are applicable to the wood-based materials mentioned in paragraph 1 even though the term "timber" has been used in the following. European Technical Assessments for structural members or wood-based panels must be considered if applicable.

The characteristic lateral load-carrying capacities and the characteristic axial withdrawal capacities of "fischer Power-Fast II" screws should be used for designs in accordance with Eurocode 5 (EN 1995-1-1) or an appropriate national code.

Reductions in the cross-sectional area caused by "fischer Power-Fast II" screws shall be taken into account in accordance to the Eurocode 5.

3.5.1 Lateral load-carrying capacity

The characteristic lateral load-carrying capacity of "fischer Power-Fast II" screws shall be calculated according to EN 1995-1-1. The contribution of the rope effect may be considered. For the calculation of the load-carrying capacity, the following parameters should be taken into account.

3.5.1.1 Embedment strength $f_{h,\alpha,k}$ for the use in Solid timber

The embedment strength for "fischer Power-Fast II" screws in non-pre-drilled holes arranged at an angle between load and grain direction, $0^{\circ} \le \alpha \le 90^{\circ}$ can be calculated with the help of equation (1).

$$f_{h,\alpha,k} = \frac{0,065 \cdot \rho_k \cdot d^{-0,3}}{k_{90} \cdot \sin^2 \alpha + \cos^2 \alpha}$$
(1)

The embedment strength for "fischer Power-Fast II" screws in pre-drilled holes arranged at an angle between screw axis and grain direction, $0^{\circ} \le \alpha \le 90^{\circ}$ can be calculated with the help of equation (2).

$$f_{h,\alpha,k} = \frac{0,065 \cdot \rho_k \cdot (1 - 0,022 \cdot d)}{k_{90} \cdot \sin^2 \alpha + \cos^2 \alpha}$$
(2)

Note: Due to the modified equations it is possible to do the total calculation to determine the shear capacity with the nominal diameter d. By doing so also in the EN 1995-1-1:2014 chapter 8.2, in the "Theorie of Johansen" the nominal diameter d should be used. As long as the core diameter d_1 is less than 6 mm the influence of the angle between load and grain direction must normally not be considered. It is also possible to carry out the calculation with the inner diameter of the thread d_1 and use the equations in clause 8.3.1 in the EN 1995-1-1:2014.

With

$$k_{90} = \begin{cases} 1,35 + 0,015 \cdot d & \text{for softwood} \\ 1,30 + 0,015 \cdot d & \text{for LVL}^* \\ 0,90 + 0,015 \cdot d & \text{for hardwood} \end{cases}$$
(3)

* made from softwood or hardwood

Where

 α Angle between load and the grain direction [°]

 $f_{h,\alpha,k}$ Characteristic embedment strength [N/mm²]

 ρ_k Characteristic timber gross density [kg/m³]

d Nominal diameter of the screw [mm];

3.5.1.2 Embedment strength $f_{h,\alpha,k}$ for the use in Cross-Laminated-Timber




Figure 1: Notations CLT-elements

- (1) Element plane
- (2) Plane surface
- (3) Edge surface (narrow side)
- (4) Inner layer (lamellas)
- (5) Outer layer (lamellas)
- (6) Middle layer (lamella)

If there are no other technical specification (ETA or hEN) for CLT, the embedment strength for screws can be calculated as following. The following specifications are only for screws with a diameter of at least 6 mm, otherwise possible influences of gaps between the single lamellas have to be considered.

Screws in the plane surface

The embedment strength for screws in the plane surface of CLT-elements should be assumed as for solid timber according to equation (1) or (2), based on the characteristic density of the outer layer. If relevant, the angle between force and grain direction of the outer layer should be considered.

Screws in the narrow (edge) side

The embedment strength for screws in the narrow side of CLT-elements should be assumed according to equation (4).

$$f_{h,k} = 20 \cdot d^{-0.5} \tag{4}$$

3.5.1.3 Embedment strength $f_{h,\alpha,k}$ for the use in LVL (ETA-14/0354)

The embedment strength for "fischer Power-Fast II" screws with $d \ge 5$ mm arranged at an angle between load and grain direction, $0^{\circ} \le \alpha \le 90^{\circ}$ can be calculated with the help of equation (5) in direction 90|90 (see figure 2).

$$f_{h,\alpha,k} = \frac{f_{h,0,k}}{(0,9+0,037 \cdot d) \cdot \sin^2 \alpha + \cos^2 \alpha}$$
(5)

With

d = 5,0 mm: $f_{h,0,k} = 50,0 \text{ N/mm}^2$ d = 6,0 mm: $f_{h,0,k} = 46,0 \text{ N/mm}^2$

3.5.1.4 Effective number of screws per row nef

For laterally loaded screws, the rules for multiple fastener connections in EN 1995-1-1 should be applied.

3.5.2 Yield strength $f_{y,Rk}$

The characteristic yield strength of the different screw types of "fischer Power-Fast II" can be taken into account as shown below.

$$f_{y,Rk} = 1050 \text{ N/mm}^2$$
 (6)

3.5.3 Yield moment M_{y,Rk}

The characteristic yield moment shall be calculated with the help of equation (7)

$$M_{\nu Rk} = 0.15 \cdot 600 \cdot d^{2.65} \tag{7}$$

Where

 $M_{y,Rk}$ Characteristic yield moment [Nmm]dNominal diameter of the threaded part
[mm]

3.5.4 Axial withdrawal capacity

The axial withdrawal capacity is limited by the head pull-through capacity, the withdrawal capacity and the tensile or compressive capacity of the screw. For "fischer Power-Fast II" fully threaded screws, the withdrawal capacity of the thread in the member with the head may be taken into account instead of the head pull-through capacity.

3.5.4.1 Withdrawal capacity $F_{ax,\alpha,Rk}$ Solid timber and Glued Laminated, Timber (EN 338, EN 14080) and LVL (ETA-14/0354)

The characteristic withdrawal capacity in softwood of "fischer Power-Fast II" screws with an angle of $0^{\circ} \le \alpha \le 90^{\circ}$ shall be calculated according to equation (8). For screws with an outer diameter d $\le 5,0$ mm equation (8) is only valid for $45^{\circ} \le \alpha \le 90^{\circ}$.

$$F_{ax,\alpha,Rk} = n_{ef} \cdot k_{ax} \cdot f_{ax,90,k} \cdot d \cdot l_{ef} \cdot \left(\frac{\rho_k}{350}\right)^{0.8}$$
(8)

With

$$k_{ax} = \min \begin{cases} 0,3 + (0,7 \cdot \alpha) / 45^{\circ} \\ 1,00 \end{cases}$$
(9)

According to equation (10) the point side penetration length has to be considered between the following range.

$$l_{ef} = \min \begin{cases} \frac{4 \cdot d}{\sin \alpha} \\ 20 \cdot d \end{cases}$$

(10) Where

d Outer thread diameter [mm]

 l_{ef} Penetration length of the threaded part according to EN 1995-1-1; For fully threaded screws the thread length including the head length in [mm]

 α Angle between grain and screw axis [°]

- ρ_k Characteristic timber gross density, maximum 730 kg/m³ [kg/m³]
- $F_{ax,\alpha,Rk}$ Characteristic withdrawal capacity of the screw with an angle α to the grain [N]
- n_{ef} Effective number of screws according to EN 1995-1-1:2014
- $f_{ax,90,k}$ Characteristic withdrawal parameter as following.

Power-Fast II	in solid timber or					
	glued laminated timber					
d= 3,0 mm	$f_{ax,90,k} =$	15,5 N/mm ²				
d= 3,5 mm	$f_{ax,90,k} =$	14,9 N/mm ²				
d= 4,0 mm	$f_{ax,90,k} =$	14,5 N/mm ²				
d= 4,5 mm	$f_{ax,90,k} =$	14,1 N/mm ²				
d= 5,0 mm	$f_{ax,90,k} =$	13,8 N/mm ²				
d= 6,0 mm	$f_{ax,90,k} =$	12,9 N/mm ²				




Figure 2: Power-Fast II in hardwood LVL

The characteristic withdrawal capacity in hardwood LVL according to ETA-14/0354 of "fischer Power-Fast II" screws with an angle of $0^{\circ} \le \alpha \le 90^{\circ}$ shall be calculated according to equation (8). For screws with an outer diameter d $\le 5,0$ mm equation (8) is only valid for $45^{\circ} \le \alpha \le 90^{\circ}$.

$$F_{ax,\alpha,Rk} = n_{ef} \cdot k_{ax} \cdot f_{ax,\alpha|\alpha,k} \cdot d \cdot l_{ef} \cdot \left(\frac{\rho_k}{730}\right)^{0,8}$$
(11)

With

$$k_{ax} = \min \begin{cases} 0.3 + (0.7 \cdot \alpha) / 45^{\circ} \\ 1.00 \end{cases}$$
(12)

3.5.4.2 Withdrawal capacity *F*_{ax,Rk} EGGER Eurostrand OSB 4 TOP

The characteristic axial withdrawal capacity of "fischer Power-Fast II" screws in EGGER Eurostrand OSB 4 TOP with an angle of $\alpha = 90^{\circ}$ and a thickness of at least 12 mm can be calculated according to equation (8), with

$$f_{ax,90,OSB,Rk} = 10 \text{ N/mm}^2$$
 (13)

for "fischer Power-Fast II" screws with diameter $d \ge 5$ mm (see Egger Eurostrand OSB 4 TOP).

3.5.4.3 Withdrawal capacity $F_{ax,Rk}$ Cross laminated timber

If there are no other technical specification (ETA or hEN) for cross laminated timber (CLT), the withdrawal capacity for screws can be calculated as following.

Screws in the plane surface

The withdrawal capacity for screws with $d \ge 6$ mm in the plane surface of CLT-elements should be assumed as for solid timber according to equation (8) based on a characteristic density of equation (14), if there are no other specifications are given. If necessary gaps between the single lamellas have to be considered.

$$\rho_k = 1, 1 \cdot \rho_{lav,k} \tag{14}$$

With

 $\rho_{\text{lay},k}$ Lowest characteristic density of the lamella in the CLT-element [kg/m³]

Screws in the narrow side

The withdrawal capacity for screws in the narrow side of CLT-elements should be assumed according to equation (15).

$$F_{ax,Rk} = 20 \cdot d^{0,8} \cdot l_{ef}^{0,9}$$
(15)

Screws in the narrow side should be driven perpendicular into the grain of the lamella. The penetration length has to be at least $3 \cdot d + l_{ef}$.

If it is guaranteed that the angle between the lamellas and the screw axis is $\ge 30^{\circ}$ the characteristic withdrawal capacity from equation (15) can be increased of about 25 %.

For screws penetrating more than one layer of cross laminated timber, the different layers may be taken into account proportionally.

3.5.4.4 Effective number of screws n_{ef}

For axially loaded screws in tension, where the external force is parallel to the screw axis, the rules in EN 1995-1-1, 8.7.2 (8) should be applied.

$$n_{ef} = n^{0.9}$$
 (16)

For inclined screws in timber-to-timber or steel-to timber shear connections, where the screws are arranged under an angle $30^{\circ} \le \alpha \le 60^{\circ}$ between the shear plane and the screw axis, the effective number of screws n_{ef} should be determined with equation below.

$$n_{ef} = \max \begin{cases} n^{0.9} \\ 0.9 \cdot n \end{cases}$$
(17)

With

n Pieces of (inclined/cross pairs) screws in a row parallel to the grain

For screws as compression reinforcement or inclined screws as fasteners in mechanically jointed beams or columns $n_{ef} = n$.

3.5.5 Head pull-through capacity *f_{head,k}* Solid timber and Glued Laminated Timber (EN 338, EN 14080) and LVL (ETA-14/0354)

The characteristic head pull-through capacity of "fischer Power-Fast II" screws in solid timber can be calculate as following.

$$F_{ax,\alpha,Rk} = n_{ef} \cdot f_{head,k} \cdot d_h^2 \cdot \left(\frac{\rho_k}{350}\right)^{0.8}$$
(18)

For timber elements with a thickness of at least 20 mm, the characteristic value of the head pull-through parameter $f_{head,k}$ can be taken into account as following.

Power-Fast II	in solid timber, cross laminated						
	timber, glued laminated timber						
	and LVL						
d= 3,0 mm	$d_h=6,0 \text{ mm}$	$f_{head,k}$ =19,0 N/mm ²					
d= 3,5 mm	d _h = 7,0 mm	fhead,k=16,3 N/mm ²					
d= 4,0 mm	d _h = 8,0 mm	$f_{head,k}$ =15,0 N/mm ²					
d= 4,5 mm	d _h = 8,8 mm	$f_{head,k}$ =14,2 N/mm ²					
d= 5,0 mm	d _h = 9,8 mm	$f_{head,k}$ =13,4 N/mm ²					
d= 6,0 mm	d _h =11,8mm	$f_{head,k}$ =13,0 N/mm ²					

3.5.6 Head pull-through capacity *f*_{head,k} Wood based panels

For the following wood-based panels described in chapter 1 with a thickness of more than 20 mm the head pull-through parameter can constitute with

$$f_{head,k} = 10 \text{ N/mm}^2 \tag{19}$$

For wood-based panels with a thickness between 12 mm and 20 mm the characteristic value of the head pull-through parameter can calculate with

$$f_{head,k} = 8 \text{ N/mm}^2 \tag{20}$$

For wood based panels with a thickness of less than 12 mm the characteristic head pull-through capacity shall be calculated with $f_{head,k}=8 N/mm^2$ with a limit of 400 N complying with a minimum thickness of the wood

based panels of $1,2 \cdot d$. In addition, to apply the minimum thickness of *Table 3*.

Table 3: Minimum	thickness	of w	ood b	pased	panels
			2.4	.1 .	1

Wood based panel	Min. thickness			
wood based panel	[mm]			
Plywood	6			
Oriented Strand board OSB	8			
Solid wood panels	12			
Particleboards	8			
Cement bonded particle boards	8			
Fibreboards (hardboards and	6			
medium boards)	0			

3.5.7 Tensile capacity *f*_{tens,k}

The characteristic tensile capacity $f_{tens,k}$ of "fischer Power-Fast II" screws depending on the outer diameter is for

Power-Fast II		
d= 3,0 mm	$f_{tens,k} =$	3,2 kN
d= 3,5 mm	$f_{tens,k} =$	4,1 kN
d= 4,0 mm	$f_{tens,k} =$	5,2 kN
d= 4,5 mm	$f_{tens,k} =$	6,3 kN
d= 5,0 mm	$f_{tens,k} =$	8,9 kN
d= 6,0 mm	$f_{tens,k} =$	13,1 kN

The tear-off capacity of the screw head is greater than the tensile capacity of the screw.

3.5.8 Compression capacity

The design compressive capacity $F_{ax,Rd}$ of "fischer Power-Fast II" screws with full thread along the length embedded in timber shall be calculated as following.

 $F_{ki,Rd} = \kappa_c \cdot N_{pl,d}$

$$F_{ax,Rd} = \min \begin{cases} F_{ax,Rd} \\ F_{ki,Rd} \end{cases}$$
(21)

(22)

Where $F_{ax Rd}$

$$F_{ax,Rd}$$
According to equation (8) $F_{ki,Rd}$ According to equation (22)

With

$$\kappa_c = 1 \qquad \text{for } \lambda_k \le 0,2$$

$$\kappa_c = \frac{1}{k + \sqrt{k^2 - \overline{\lambda}^2}} \qquad \text{for } \overline{\lambda}_k > 0,2 \qquad (23)$$

 $f_{am} = \frac{1}{2} < 0.2$

and

$$k = 0,5 \cdot \left[1 + 0,49 \cdot \left(\overline{\lambda}_k - 0,2\right) + \overline{\lambda}_k^2\right]$$
(24)

The relative slenderness ratio shall be calculated with

$$\overline{\lambda}_k = \sqrt{\frac{N_{pl,k}}{N_{ki,k}}} \tag{25}$$

With the characteristic value for the axial capacity in case of plastic analysis referred to the outer thread diameter

$$N_{pl,k} = \frac{(0,7 \cdot d)^2 \cdot \pi}{4} \cdot f_{y,Rk}$$
(26)

And the characteristic ideal elastic buckling load

$$N_{ki,k} = \sqrt{c_h \cdot E_s \cdot I_s} \tag{27}$$

With the

Elastic foundation of the screw:

$$c_h = (0,19+0,0084 \cdot d) \cdot \rho_k \cdot \left(\frac{\alpha}{180^\circ} + 0,5\right)$$
 (28)

Modulus of elasticity:

$$E_{\rm s} = 210.000 \, \rm N/mm^2$$
 (29)

Second moment of area:

$$I_{s} = \frac{\pi \cdot (0, 7 \cdot d)^{4}}{64}$$
(30)

Note: The compressive capacity must be modified for $f_{ax,d}$ with the factors k_{mod} and γ_M for timber according to EN 1995-1-1 while $N_{pl,d}$ the partial-factor $\gamma_{M,1}$ for steel buckling according to EN 1993-1-1 and/or national standards respectively have to be considered.

3.5.9 Combined laterally and axially loaded screws

For connections subjected to a combination of axial and lateral load, the following expression has to be considered according to equation

$$\left(\frac{F_{ax,Ed}}{F_{ax,Rd}}\right)^2 + \left(\frac{F_{\nu,Ed}}{F_{\nu,Rd}}\right)^2 \le 1$$
(31)

With

 $F_{ax,Ed}$ Axial design action [N] $F_{v,Ed}$ Lateral design action [N] $F_{ax,Rd}$ Design load-carrying capacity of an axially
loaded screw [N]

$F_{v,Rd}$ Design load-carrying capacity of a laterally loaded screw [N]

3.5.10 Slip modulus

Laterally loaded screws

For laterally loaded "fischer Power-Fast II" screws the slip modulus predrilled or non-predrilled for the serviceability limit state (SLS) for screws could be calculated according to EN 1995-1-1:2014 independent of the angle α to the grain with equation (32).

$$K_{ser} = k_{sys} \cdot k_{sb} \cdot \frac{\rho_m^{1,5} \cdot d}{23}$$
(32)

With

 k_{sys} $k_{sys} = \begin{cases} 1 & \text{for timber-timber connections} \\ 2 & \text{for steel-timber connections} \end{cases}$ k_{sb} Number of shear bands




Figure 3: Definition shear bands

Where

 K_{ser} Slip modulus in SLS [N/mm] ρ_m Mean timber density [kg/m³]

Axially loaded screws

For axially loaded screws the slip modulus for the serviceability limit state (SLS) could be calculated independent on the angle α to the grain according to equation (33).

$$K_{ser} = 25 \cdot d \cdot l_{ef} \tag{33}$$

To consider the slip modulus K_u in the ultimate limit state (ULS) K_{ser} has to be reduced for both directions (laterally and axially) according to EN 1995-1-1.

$$K_u = 2/3 \cdot K_{ser} \tag{34}$$

3.5.12 Minimum timber cross section, end- and edge distances

For structural timber members, minimum spacing and distances for screws in predrilled holes are given in EN 1995-1-1:2014 clause 8.3.1.2 and table 8.2 as for nails

in predrilled holes. Here, the outer thread diameter d must be considered.

For screws in non-predrilled holes, minimum spacing and distances are given in EN 1995-1-1:2014 clause 8.3.1.2 and table 8.2 as for nails in non-predrilled holes.

Minimum thickness for structural members are in general t=24 mm.

3.5.12.1 Solid timber (EN 338, EN 14080)

Alternatively, minimum distances and spacing for exclusively axially loaded "fischer Power-Fast II" screws in non-predrilled holes in members of solid timber (softwood and hardwood), glued laminated timber or similar glued products (softwood and hardwood) with a minimum thickness $t = 12 \cdot d$ and a minimum width of 8·d or 60 mm, whichever is the greater, may be taken as:

Spacing a ₁ parallel to the grain of solid timber	$a_1 = 5 \cdot d$
Spacing a ₂ perpendicular to the grain of solid timber	$a_2 = 5 \cdot d$
Distance $a_{3,c}$ from centre of the screw-part in timber to the end grain of solid timber	$a_{3,c}=9\cdot d$
Distance a _{4,c} from centre of the screw-part in timber to the edge of solid timber	a. – 4.d
	$a_{4,c} = 4 \cdot d$

Spacing a_2 perpendicular to the grain may be reduced from 5·d to 2,5·d, if the condition $a_1 \cdot a_2 \ge 25 \cdot d^2$ is fulfilled. For Douglas fir members minimum spacing and distances parallel to the grain shall be increased by 50%.

Minimum distances from the unloaded edge perpendicular to the grain may be reduced to $3 \cdot d$ also for timber thickness t < $5 \cdot d$, if the spacing parallel to the grain and the end distance is at least $25 \cdot d$.

3.5.12.2 Cross Laminated Timber

Unless specified otherwise in the technical specification (ETA or hEN) of cross laminated timber (CLT), minimum distances and spacing for screws in the plane surface of cross laminated timber members with a minimum thickness $t = 10 \cdot d$ may be taken as (see Annex B2).

Spacing a_1 parallel to the grain of	4 1
the CLT-plane surface	$a_1 = 4 \cdot d$
Spacing a ₂ perpendicular to the	
grain of the CLT-plane surface	$a_2 = 2,5 \cdot d$
Distance a _{3,c} from centre of the	
screw-part in CLT to the unloaded	
end grain of the plane surface	$a_{3,c}=6\cdot d$
Distance a _{3,t} from centre of the	
screw-part in CLT to the loaded	
end grain of the plane surface	$a_{3,t} = 6 \cdot d$
Distance a _{4,c} from centre of the	
screw-part in CLT to the unloaded	
edge of the plane surface	$a_{4,c} = 2,5 \cdot d$
Distance a _{4,t} from centre of the	
screw-part in CLT to the loaded	
edge of the plane surface	$a_{4,t} = 6 \cdot d$

Unless specified otherwise in the technical specification (ETA or hEN) of cross laminated timber, minimum distances and spacing for screws in the edge surface of cross laminated timber members with a minimum thickness t = 10 d and a minimum penetration depth perpendicular to the edge surface of 10 d may be taken as (see Annex B2):

Spacing a ₁ parallel to the CLT edge surface	$a_1 = 10 \cdot d$
Spacing a ₂ perpendicular to the CLT edge surface	$a_2 = 4 \cdot d$
Distance $a_{3,c}$ from centre of the screw- part in CLT to the unloaded end grain of the edge surface	$a_{3,c} = 7 \cdot d$
Distance $a_{3,t}$ from centre of the screw- part in CLT to the loaded end grain of the edge surface	$a_{3,t} = 12 \cdot d$
Distance a _{4,c} from centre of the screw- part in CLT to the unloaded edge surface	$a_{4,c} = 3 \cdot d$
Distance a _{4,t} from centre of the screw- part in CLT to the loaded edge surface	$a_{4,t} = 6 \cdot d$

For a crossed screw couple the minimum spacing between the crossing screws is $1,5 \cdot d$.

3.6 Aspects related to the performance of the product

3.6.1 Corrosion protection in service class 1 and 2

The "fischer Power-Fast II" screws are produced from carbon steel. They are zinc-plated (e.g. yellow-zinced or blue-zinced), bonus-zinc-coated, burnished, nickel-plated or brass-plated. The mean thickness of the zinc-plated screws is min. 5 μ m.

3.7 General aspects related to the intended use of the product


The screws are manufactured in accordance with the provisions of the European Technical Assessment using the automated manufacturing process as identified during the inspection of the plant by the assessment body issuing the ETA and the notified body and laid down in the technical documentation. The installation shall be carried out in accordance with Eurocode 5 or an appropriate national code unless, otherwise defined in the following.


4 Attestation and verification of constancy of performance (AVCP)


4.1 AVCP system

According to the decision 97/176/EC of the European Commission1, as amended, the system(s) of assessment and verification of constancy of performance (see Annex V to Regulation (EU) No 305/2011) is 3.

Appendix 12 / 22










Appendix 14 / 22

Power-Fast II - Self-drilling screw - Pan head with full- or partial thread															
						ls ²⁾									
			-	•		lgf		-							
	U	Inderhead nilling pocl	kets ¹⁾	-								ade mark-	~		
			ť	6											
	E PARTICICAL STOR												60.)	
			I L	/		~ ~ ~ ~ ~	lgp								
Shank ribs ¹⁾ Coremiller ¹⁾															
¹⁾ optional Figure not to scale															
	bon Ste sible s		reatments:					lated, b	lue zinc·	-plated 2	≥12µm,	bonus-z	inc-coa	ted, bur	nished,
Nor	ninal	diame	tor		plated, t			4	0	4	5	L 6	0	6	0
			t er liameter		,0 00		,5 50		,0 00		,5 50		,0 00		,0 00
d —		deviatio		± 0),25	± 0	,25	± 0	,30		,30		,30	± 0	,30
d4 —		hread di			95		20		50		75		25		95
		deviatio diamete),18 00		0,18 00		,20 00		,20 00		,20 ,00		,20 ,00
d h –		deviatio),50	-	,50		00 ,60		,60		,60 ,60		,60 ,60
d- –		diamete			25		60		90		20		70		30
-	Allow. Head I	deviatio	on),15 30		,15 50		,15 80		,15 80		,15 40		,15 40
		ve TX			0	10	20		20		0	20	25		0
		ve PZ			1		2		2		2		2	3	
		ength l	s ²⁾	Star	ndard th	read le	ength I	l _{gf} = Ful	l threac	1 l _{gp} =	Partial	thread	Tolera	nce: ±	2,0 ³⁾
Nomin lengtl		min	max	l _{gf}	l _{gp}	l _{gf}	l _{gp}	l _{gf}	l _{gp}	l _{gf}	l _{gp}	l _{gf}	l _{gp}	l _{gf}	l _{gp}
20 25		<u>, –1,05</u>	ls +1,05	16 21	18	16 21	18	20	18	20					
30		<u>, –1,25</u> , –1,25	l₅ +1,25 l₅ +1,25	21	18	21	18	20	18	20	18	24			
35		s —1,50	ls +1,50	31	24	31	24	30	24	30	24	29	24	28	
40		s –1,50	ls +1,50	36	28	36	28	35	28	35	28	34	28	33	28
45 50		<u>,</u> –1,50 , –1,50	l₅ +1,50 l₅ +1,50	41	30	41 46	30 30	40 45	30 30	40 45	30 30	39 44	30 30	38 43	30 30
55		, <u>1,86</u> , –1,75	ls +1,75					50	36	50	36	49	36	48	48
60		, –1,75	ls +1,75					55	36	55	36	54	36	53	36
70 80		<u>-1,75</u>	l₅ +1,75 l₅ +1,75						42 45	65 75	42 45	64 74	42 45	63 73	42 45
90			$l_{s} + 1,73$ $l_{s} + 2,00$						40	15	40	/ +	45 54	13	45 54
100		, –2,00											60		60
110			ls +2,00										70		70
120 in		<u>-2,00</u> of 10mr	l₅ +2,00 m										70		70
130-30		s –3,00													70
Table A	3.1: Sc	rew size	es and mat	terial									All	sizes in	mm
²⁾ Other length	r screw ns are a	lengths allowed	l thread > with l₅ mi ,l _{gp} ≤ 18mi	n ≤ l₅ ≤	l₅ max a	and othe	er thread								
	fischer Power-Fast II										ļ	Annex	A3		
Screw sizes and material															







Design of the battens

The bending stresses of the battens are calculated with

$$M_{Ed} = \frac{\left(F_{Ed} + F_{s,Ed}\right) \cdot l_{char}}{4}$$

****/h

Where								
F _{Ed} F _{s,Ed} M _{Ed} l _{char}	Point loads perpendicular to the battens [N] Point loads perpendicular to the battens in the area of the so Design bending moment of the batten [Nmm] Characteristic length of the batten [mm]	rew heads [N]						
	with $l_{char} = \sqrt[4]{\frac{4 \cdot EI}{w_{ef} \cdot K}}$, where							
	EIBending stiffness of the batten [Nmm²] w_{ef} Effective width of the thermal insulation [mm]with $w_{ef} = w + t_{ti} / 2$, where							
	w Mimimum width of the batten or rafter [mm] t_{ti} Thickness of the thermal insulation [mm] K Bedding modulus [N/mm³]The coefficient K may be calculated from the mo E_{ti} and the thickness t_{ti} of the thermal insulation ifwidth w_{ef} of the thermal insulation under compreseDue to the load extension in the insulation the effective width w_{ef} of thegreater than the width of the batten or rafter, respfurther calculations, the effective width w_{ef} of the	the effective sion is known. fective width w_{ef} is pectively. For						
	may be determined with $K = \frac{E_{ti}}{t_{ti}}$, where							
	E_{ti} Modulus of elasticity of the thermal insulation [N/mm ²] t_{ti} Thickness of the thermal insulation [mm]							
The follo	wing conditions shall be satisfied:							
a) Where	$\frac{\sigma_{m,Ed}}{f_{m,d}} \leq 1$							
$\sigma_{m,Ed}$ $f_{m,d}$	Design value of the bending stress of the batten [N/mm²] Design value of the bending strength [N/mm²]							
b)	$\frac{\tau_{Ed}}{f_{v,d}} = \frac{3 \cdot V_{Ed}}{2 \cdot A_{ef} \cdot f_{v,d}} \le 1$							
Where $f_{v,d}$ A_{ef} V_{Ed}	Design value of the shear strength of the batten [N/mm ²] Net cross section of the batten [mm ²] Design shear load onto the batten [N] with $V_{Ed} = \frac{F_{Ed} + F_{s,Ed}}{2}$							
$ au_{Ed}$	² Design value of the shear stress of the batten [N/mm²]							
	fischer Power-Fast II	Annex B1.4						
	Fixing of on-roof insulation							

Design of the heat insulation

The compressive stresses in the thermal insulation shall be calculated with

$$\sigma_{c,Ed} = \frac{1, 5 \cdot F_{Ed} + F_{s,Ed}}{2 \cdot l_{char} \cdot w_{ef}}$$

Where

	fischer Power-Fast II Fixing of on-roof insulation	Annex B1.4					
	fieches Devus East !!	Annex B1.4					
	sign value of the compressive stress shall not be greater thar % deformation calculated according to EN 826.	110 % of the compressive					
$\sigma_{\!\scriptscriptstyle c,Ed}$	t_{ti} Thickness of the thermal insulation [mm] Design value of the compression stresses of the thermal insu $\sigma_{c,Ed}$	ulation					
	may be determined with $K = \frac{E_{ti}}{t_{ti}}$, where E_{ti} Modulus of elasticity of the thermal insulation [N/mm ²]						
	further calculations, the effective width w_{ef} of the f						
	E_{ti} and the thickness t_{ti} of the thermal insulation if width w_{ef} of the thermal insulation under compres Due to the load extension in the insulation the eff greater than the width of the batten or rafter, resp	sion is known. Tective width w_{ef} is					
	 <i>w</i> Mimimum width of the batten or rafter [mm] <i>t_{ii}</i> Thickness of the thermal insulation [mm] <i>K</i> Bedding modulus [N/mm³] The coefficient <i>K</i> may be calculated from the modulum insulation [mm] 						
	<i>EI</i> Bending stiffness of the batten [Nmm ²] w_{ef} Effective width of the thermal insulation [mm] with $w_{ef} = w + t_{ti} / 2$, where						
	with $l_{char} = \sqrt[4]{\frac{4 \cdot EI}{w_{ef} \cdot K}}$, where						
F_{Ed} $F_{s,Ed}$ l_{char}	Point loads perpendicular to the battens in the area of the screw heads [N] Characteristic length of the batten [mm]						

Design of the screws

The screws are loaded predominantly axially. The axial tension force in the screw may be calculated from the shear loads of the roof

$$F_{ax,Ed} = \frac{R_{s,Ed}}{\cos \alpha_r} \le F_{ax,\alpha,Rd}$$

Where

 $F_{ax,Ed}$ Design value of the axial tension forces onto the screw [N] $F_{ax,\alpha,Rd}$ Design value of the withdrawal capacity of the screw [N] $R_{s,Ed}$ Shear loads onto the screw [N] α_r Angle inclined screw (see figure B1.3) [°]

The load-carrying capacity of axially loaded screws is the minimum design value of the axial withdrawal capacity of the threaded part of the screw, the head pull-through capacity of the screw and the tensile capacity of the screw.

In order to limit the deformation of the screw head for heat insulation thicknesses over 200 mm or with compressive strength below $0,12 \text{ N/mm}^2$, respectively, the axial withdrawal capacity of the screws shall be reduced by the factors k_1 and k_2 .

$$F_{ax,\alpha,Rd} = \min\left\{k_{ax} \cdot f_{ax,d} \cdot d \cdot l_{ef} \cdot k_1 \cdot k_2 \cdot \left(\frac{\rho_k}{350}\right)^{0,8}, f_{head,d} \cdot d_h^{-2} \cdot \left(\frac{\rho_k}{350}\right)^{0,8}, f_{tens,d}\right\}$$

Where

$F_{ax, \alpha, Rd}$	Design value of the withdrawal capacity of the screw [N]
d	Diameter of the screw [mm]
d_h	Head diameter of the screw [mm]
$f_{ax,d}$	Design value of the withdrawal parameter of the threaded part of the screw [N/mm ²]
fhead,d	Design value of the head pull-through capacity of the screw [N/mm ²]
$f_{tens,d}$	Design value of the tensile capacity of the screw [N]
<i>k</i> _{ax}	Coefficient according to equation (8)
k_{I}	$min \{1; 200 / t_{ii}\}$ [-]
k_2	min {1; $\sigma_{10\%,Ed}/0,12$ } [-], where
	$\sigma_{10\%,Ed}$ Compressive stress of the heat insulation at 10 % deformation [N/mm ²]
	<i>t_{ti}</i> Thickness of the thermal insulation [mm]
l_{ef}	Point side penetration length of the threaded part in the rafter with $l_{ef} \ge 40$ mm [mm]
α	Angle between grain and screw axis ($\alpha \ge 30^\circ$) [°]
$ ho_k$	Characteristic density of the timber element [kg/m³]

Note: If in the equation for $F_{ax,Rd}$ the factors k_1 and k_2 are considered, the deflection of the battens does not need to be considered. Alternatively to the battens, panels with a minimum thickness of 20 mm from plywood according to

EN 636 or an ETA or national provisions that apply at the installation site, particle board according to EN 312 or an ETA or national provisions that apply at the installation site, oriented strand board according to EN 300 or an ETA or national provisions that apply at the installation site and solid wood panels according to EN 13353 or an ETA or national provisions that apply at the installation site or cross laminated timber according to an ETA may be used.

fischer Power-Fast II	Annex B1.5
Fixing of on-roof insulation	

Thermal insulation material on rafters with parallel screws perpendicular to the roof plane

Alternatively to the battens, panels with a minimum thickness of 20 mm from plywood according to EN 636, particleboard according to EN 312, oriented strand board OSB/3 and OSB/4 according to EN 300 or European Technical Approval and solid wood panels according to EN 13353 may be used.

Characteristic load-carrying capacity of a screw loaded in shear:

$$F_{v,Rk} = \min \begin{cases} f_{h,b,k} \cdot d \cdot t_{b} \\ f_{h,r,k} \cdot d \cdot t_{r} \\ \frac{f_{h,b,k} \cdot d \cdot \beta}{1+\beta} \cdot \left(\sqrt{4t_{ti}^{2} + (2+\frac{1}{\beta})t_{b}^{2} + (2+\beta)t_{r}^{2} + 4t_{ti}(t_{b} + t_{r}) + 2t_{b}t_{r}} - 2t_{ti} - t_{b} - t_{r}\right) + \frac{F_{ax,Rk}}{4} \\ 1,05 \cdot \frac{f_{h,b,k} \cdot d \cdot \beta}{\frac{1}{2} + \beta} \left(\sqrt{t_{ti}^{2} + t_{ti}t_{b} + \frac{t_{b}^{2}}{2}\left(1 + \frac{1}{\beta}\right) + \frac{M_{y,k}}{f_{h,b,k} \cdot d}\left(1 + \frac{2}{\beta}\right)} - t_{ti} - \frac{t_{b}}{2}\right) + \frac{F_{ax,Rk}}{4} \\ 1,05 \cdot \frac{f_{h,b,k} \cdot d \cdot \beta}{\frac{1}{2} + \beta} \left(\sqrt{t_{ti}^{2} + t_{ti}t_{r} + \frac{t_{r}^{2}}{2}(1 + \beta) + \frac{M_{y,k}}{f_{h,b,k} \cdot d}\left(2 + \frac{1}{\beta}\right)} - t_{ti} - \frac{t_{r}}{2}\right) + \frac{F_{ax,Rk}}{4} \\ 1,15 \cdot \frac{f_{h,b,k} \cdot d}{1+\beta} \left(\sqrt{\beta^{2}t_{ti}^{2} + 4 \cdot \beta(\beta + 1) \cdot \frac{M_{y,k}}{f_{h,b,k} \cdot d}} - \beta \cdot t_{ti}\right) + \frac{F_{ax,Rk}}{4} \end{cases}$$

Where

fischer Power-Fast II Annex B1.6	$F_{v,RK}$ $M_{y,k}$ $F_{ax,Rk}$ $f_{h,b,k}$ $f_{h,r,k}$ d t_{b} t_{r} t_{ti} β	Characteristic load-carrying capacity of a screw loaded in sh Characteristic yield moment of the screw [Nmm] The minimum characteristic load-carrying capacity of the axis screws acc. to EN 1995-1-1 [N] Characteristic embedment strength of the batten [N/mm ²] Characteristic embedment strength of the rafter [N/mm ²] Outer thread diameter [mm] Batten thickness [mm] The lower value of rafter thickness or screw penetration leng Thickness of the thermal insulation [mm] Coefficient of the embedment strength of the rafter to the bat with $\beta = \frac{f_{h,r,k}}{f_{h,b,k}}$	ally loaded th [mm]
		fischer Power-Fast II	Annex B1.6
Fixing of on-roof insulation		Fixing of on-roof insulation	





Table B2.1: Minimum spacing, end and edge distances of screws in the **plane surfaces** of cross laminated timber

	a ₁	a _{3,t}	a _{3,c}	a ₂	a _{4,t}	a _{4,c}
Plane surface	4 · d	6 · d	6 · d	2,5 · d	6 · d	2,5 · d

Definition of spacing, end and edge distances in the **edge surface** (narrow side) unless otherwise specified in the technical specification (ETA or hEN) for the cross laminated timber.








Table B2.2: Minimum spacing, end and edge distances of screws in the **edge surfaces** (narrow side) of cross laminated timber

	a ₁	a _{3,t}	a _{3,c}	a ₂	a _{4,t}	a _{4,c}
Edge surface	10 · d	12 · d	7 ⋅ d	$4 \cdot d$	6 · d	3 · d

fischer Power-Fast II	Annex B2
Minimum distance and spacing	